



## CHARACTERISTICS

- Adhesive
- Permanent elasticity
- Very easy to apply
- Does not cause staining on natural stone
- High resistance to UV
- Can be applied to dry and slightly damp surfaces
- Very high initial bonding strength ('high tack')
- Does not cause any corrosion in metal joints
- Paintable with most water and solvent based paints
- High resistance to ageing and weather conditions
- Solvent, isocyanate and phthalate free
- Tin free
- Low odour

## APPLICATIONS

- Bonding and assembling everything.
- Indoor and outdoor use.

## TECHNICAL CHARACTERISTICS

|   |   |
|---|---|
| Type of product   | Hybrid polymer  |
| Density (g/ml)  | 1.43  |
| Number of components                                      | 1   |
| Application temperature                                   | +5°C - +40°C  |
| Temperature resistance                                    | -40°C - +90°C   |
| Curing system   | Cross-linking by air humidity   |
| Curing speed at 23 degrees C and 50% R.H. (mm, after 24h) | 2 - 3   |
| Skin forming time at 23°C and 50% R.H. (min.)             | 15  |
| Shore A hardness: ISO 868                                 | 63  |
| Modulus at break: ISO 8339 (N/mm <sup>2</sup> )           | 1.26  |
| % Elongation at break: ISO 8339                           | 45  |
| Dry matter content  | ±100%   |
| Shelf life of unopened product                            | 12 months   |
| Storage conditions  | Store in a dry, cool place at +5°C to +25°C. Keep out of direct sunlight. |

## PACKING AND COLOURS

**12 x cartridge 290ML/box - 1200 pieces/pallet**  
White, Black

## METHOD OF USE

### Preparation

- The surface must be solid, strong enough and clean, dust and fat-free.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

- If needed degrease the materials to be glued with Parasilico Cleaner, MEK, fire alcohol, ethanol.
- Use in well-ventilated rooms. Good ventilation is important during application and curing of the product.
- The user needs to make sure that the product is suitable for the application. Consult our technical service if necessary.
- Remove any water, water film or raindrops. The best adhesion is obtained on a dry surface.

### Primers

- On highly absorbent surfaces we recommend to use the Hybrid & PU Primer (transparent or black, drying time about 15 min.).

### Application

- Apply the product with the nozzle in strips or dots to the base or on the element to be bonded. The strips must be applied in vertical rows and parallel to each other, to allow the humidity to reach the adhesive between the strips.
- Bring together the parts to be joined as quickly as possible, at least within 10 minutes (depends on the temperature and relative humidity). The parts can at this stage still be adjusted. Finally, push down well or tap with a rubber hammer.
- It is advised to have a gap of 3.2 mm between the parts to be bonded spacer blocks or pieces of foam tape may be used), to allow the adhesive to smooth out any distortions (especially important in exterior use or under humid conditions).
- The internal strength immediately after application is such that bonding is possible without clamping or temporary support.

### Cleaning

- Any adhesive that may protrude along the edges can be removed using a stopping knife. Adhesive residue that has not yet dried, can be removed using Parasilico Cleaner, Multi-Purpose Super Cleaner or Cleaning Wipes.
- After curing remove mechanically.

### Paintable

- Paintable after curing with most water and solvent based paints. Curing time depends on the joint dimensions.
- After 48 hours, the surface must be cleaned first before it can be painted.
- Given the wide variety of paint types available, it is recommended that you test the compatibility of the sealant/adhesive with the paint in advance.
- Alkyd paints might require an extended drying time.

## SAFETY

Consult the safety information on the packaging and the safety data sheet for more information.

## POINTS OF ATTENTION

- Not suitable for permanent submersion.
- Not suitable for use on butiminous surfaces.
- Not suitable for use on PE, PP, PA, PTFE (Teflon).
- Not suitable for use on polyacrylate and polycarbonate
- Not suitable for glazing joints.
- Not suitable for contact with edge sealing of insulating glazing. Avoid direct contact.
- Not suitable for contact with PVB films of laminated glass. Avoid direct contact.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply

## TECHNICAL APPROVALS

- French VOC emission class A+



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply